



ULTRATECH
INTERNATIONAL, INC.



Specifications

Ultra-Containment Berm 18 oz. PVC



Typical Properties

Base Fabric Type	Polyester
Base Fabric Weight (nominal)	5.0 oz/yd ²
Finished Coated Weight ASTM D751	18 oz/yd ² +2/-1 oz/yd ²
Tongue Tear ASTM D751	8" x 10" sample @12"/minute 80/80 lb _f
Grab Tensile ASTM D751	375/350 lb _f
Strip Tensile ASTM D751 Procedure B	300/275 lb _f /in
Adhesion ASTM D751 RF Weld	10 lbf /in minimum
Hydrostatic Resistance ASTM D751 Procedure A	500 psi
Low Temperature ASTM D2136	1/8 in mandrel, 4 hr Pass @-40° F
Working Temperature Range ASTM D2136	-20°F to 160° F
Flame Resistance FMVSS302	Pass 4 in/min
Roll Specifics	Width up to 75 in. Length 110 yd.
<p>Unless stated otherwise, values presented above represent the minimum expected measurements at the time of manufacture. We believe this information is the best currently available on the subject. We offer it as a suggestion in any appropriate experimentation you may care to undertake. It is subject to revision as additional knowledge and experience are gained. We make no guarantee of results and assume no obligation or liability whatsoever in connection with this information.</p> <p>Issued November 2006</p>	