

Chemical Storage Tank Compatibility

Safe storage of chemicals requires selecting the right materials for your liquid storage tank. Selecting the wrong one tank type for your chemical could cause a loss of product, time, and money. It can also cause risk to your employees or equipment. However, picking the right material for your tank ensures safe storage and a long use-life.



No matter what type of tank you need or how you plan to use it, we have well-made, durable and affordable options. Let us help you. Call us (+1) 863-261-8388!

(A)-Resistant, no indication that serviceability would be impaired. **(B)**-Variable resistance, depending on conditions of use. **(C)**-Unresistant, not recommended for service applications under any conditions. **(-)** Information not yet available. FOB Codes: **N**=NY, **T**=TX, **I**=IL, **C**=CA, **F**=FL, **P**=PA, **H**=HI, **Tn**=TN

REAGENT	CONC.	TANK MATERIALS						FITTING MATERIALS							
		LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Acetone		C	C	A	A	C	C	C	C	C	C	C	A	A	A
Acetaldehyde*	100%	B	C	A	B	B	C	C	C	A	C	C	A	A	A
Acetic Acid*	10%	A	A	A	A	A	A	A	A	A	A	B	A	A	A
Acetic Acid*	60%	A	B	A	A	A	A	A	A	A	B	B	A	A	A
Acetic Anhydride*		C	C	C	C	C	C	B	A	C	A	A	A
Air		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Aluminum Chloride	all concentr.	A	A	A	A	A	A	A	A	A	A	A	C	B	A
Aluminum Fluoride	all concentr.	A	A	A	A	A	A	A	A	A	A	A	C	A	B
Aluminum Sulphate	all concentr.	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Alums	all types	A	A	A	A	A	A	A	A	A	A	A	A	...	A
Ammonia	100% dry gas	A	A	A	A	A	A	B	A	A	A	A	A	C	A
Ammonium Carbonate		A	A	A	A	A	A	A	A	A	A		B	A	B
Ammonium Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	C	B	A
Ammonium Fluoride	sat'd	A	A	A	A	A	A	A	A	B	A	A	C	A	A
Ammonium Hydroxide	10%	A	A	A	A	A	A	A	A	B	A	B	A	A	B
Ammonium Nitrate	sat'd	A	A	A	A	A	A	A	A	A	B	A	A	A	B
Ammonium															
Persulphate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Ammonium Sulphate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B

REAGENT	TANK MATERIALS							FITTING MATERIALS							
	CONC.	LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Ammonium															
Metaphosphate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Ammonium Sulfide	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Amyl Acetate*#	100%	C	C	B	C	C	C	C	C	A	C	C	A	A	A
Amyl Alcohol*#	100%	A	A	A	B	A	A	A	A	A	A	B	A	B	A
Amyl Chloride*#	100%	C	C	C	C	C	C	C	C	C	C	B	A	C	A
Aniline*#	100%	C	C	A	A	A	C	C	C	B	C	C	B	C	B
Aqua Regia +		C	C	C	C	C	C	C	C	C	C	B	C	A	C
Arsenic Acid	all concentr.	A	A	A	A	A	A	A	A	A	A	A	A	B	B
Aromatic															
Hydrocarbons *#		C	C	C	C	C	C	C	C	A	C
Ascorbic Acid	10%	A	A	A	A	A	A	A	A	A	A	A
Barium Carbonate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Barium Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	B
Barium Hydroxide		A	A	A	A	A	A	A	A	A	A	A	B	B	A
Barium Sulphate	sat'd	A	A	A	A	A	A	B	B	A	A	A	B	B	...
Barium Sulphide	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	A
Beer		A	A	A	A	C	C	A	A	A	C	A	A	B	B
Benzene*#		C	C	B	C	C	C	C	C	C	C	A	B	A	B
Benzoic Acid	all concentr.	A	A	A	A	A	A	A	A	C	A	A	B	B	A
Bismuth Carbonate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	B
Bleachlye	10%	A	A	A	A	A	A	A	A	A	A	A	A	B	B
Borax	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	B	A
Boric Acid	all concentr.	A	A	A	A	A	A	A	B	A	A	A	A	A	A
Boron Trifluoride		A	A	A	A	A	A	A	A	A	...	B	...
Brine		A	A	A	A	A	A	A	A	A	A	A	C	A	A
Bromine +	liquid	C	C	C	C	C	C	C	C	C	C	A	C	A	A
Bromine Water #	sat• d	C	C	C	...	C	C	C	C	C	C	A	C	A	A

REAGENT	TANK MATERIALS							FITTING MATERIALS							
	CONC.	LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Butanediol*	10%	A	A	A	A	A	A
Butanediol*	60%	A	A	A	A	A	A
Butanediol*	100%	A	A	A	A	A	A
Butter*		A	A	A	A	C	C	...	A	A	B	A	A
n-Butyl Acetate*#	100%	A	C	C	C	A	C	C	B	B	C	B	B	A	A
n-Butyl Alcohol	100%	A	A	A	...	A	A	A	B	B	A	A	A	A	A
Butyric Acid #	conc.	C	C	B	B	B	C	B	B	A	A
Calcium Bisulphide		A	A	A	A	A	A	A	A	A	A	A	B	A	...
Calcium Carbonate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	B	B
Calcium Chlorate	sat'd	A	A	A	A	A	A	A	A	A	...	A
Calcium Chloride	sat'd	A	A	A	A	A	A	A	A	B	A	A	B	A	A
Calcium Hydroxide	conc.	A	A	A	A	A	A	A	A	B	C	A	B	A	B
Calcium Hypochlorite	bleach sol'n	A	A	A	B	B	B	B	B	A	C	A	C	...	B
Calcium Nitrate	50%	A	A	A	A	A	A	A	A	A	B	A	A	A	
Calcium Oxide	sat'd	A	A			A	A	A	A	A	A	A	A	A	A
Calcium Sulphate		A	A	A	A	A	A	A	A	A	C		B	A	A
Camphor Oil*#		C	C	C	C	C	C					A	A		
Carbon Dioxide	all concentr.	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Carbon Disulphide		C	C	B	C	C	C	C	C	C	C	A	B	B	B
Carbon Monoxide		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Carbon Tetrachloride#		C	C	C	C	C	C	B	C	C	C	A	B	A	A
Carbonic Acid		A	A	A	A	A	A	A	A	A	A	A	A	B	A
Caster Oil #	conc.	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Chlorine +	100% dry gas	C	C	C	C	B	C	C	C	C	C	A	C	C	B
Chlorineliquid +		C	C	C	C	C	C	A	A	C	C	A	C	A	A
Chlorine Water +	2% sat'd sol'n	A	A	A	B	A	A	A	A	C	C	A	C	A	A

TANK MATERIALS		FITTING MATERIALS													
REAGENT	CONC.	LDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		LMDPE	HDPE	70°	140°	70°	140°	70°	140°						
Chlorobenzene*#		C	C	C	C	C	C	C	C	C	C	A	A	A	B
Chlorofoam*#		B	C	C	C	C	C	C	C	C	C	A	A	A	A
Chlorosulphonic Acid	100%	C	C	C	C	C	C	C	C	C	C	C	B	C	A
Chrome Alum	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Chromic Acid	80%	A	C	C	C	C	B	B	C	B
Chromic Acid	50%	A	B	A	A	A	B	B	B	B	C	A	B	C	B
Chromic Acid	10%	A	A	A	A	A	A	A	A	B	C	A	B	C	B
Cider*		A	A	A	A	C	C	A	A	A	A	...
Citric Acid*	sat'd	A	A	A	A	A	A	...	B	A	A	A	A	A	A
Coconut Oil Alcohols*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Coffee		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Cola Concentrates*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Copper Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	C	A	A
Copper Cyanide	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	B	B
Copper Fluoride	2%	A	A	A	A	A	A	A	A	A	...	A	A	A	A
Copper Nitrate	sat'd	A	A	A	A	A	A	A	A	...	A	A	B	B	A
Copper Sulphate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	A
Corn Oil*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Cottonseed Oil*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Cuprous Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	C	A	A
Detergents, Synthetic* Developers, Photographic		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Dextrin	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Destrose	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Diazo Salts		A	A	A	A	A	A	A	A
Dibutylphthalate*#		B	B	A	B	B	B	C	C	A
Dichlorobenzene*#		C	C	C	C

REAGENT	TANK MATERIALS							FITTING MATERIALS							
	CONC.	LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Diethyl Ketone*#		B	B	B	C
Diethylene Glycol*		A	A	A	A	A	A	C	C	A	A	A	A	A	B
Diglycolic Acid*		A	A	A	A	A	A	A	...	A	A	A	...
Dimethylamine		C	C	C	C	C	C	C	A	C	A
Disodium Phosphate		A	A	A	A	A	A	A	A	A	A	A	...
Emulsions, Photographic*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyl Acetate*#	100%	B	C	B	B	B	C	C	C	B	C	C	A	A	A
Ethyl Alcohol*	100%	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyl Alcohol*	35%	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Ethyl Benzene*#		C	C	C	C	C	C	A
Ethyl Chloride #		C	C	C	C	C	C	C	C	A	B	A	A	A	A
Ethyl Ether #		C	C	B	C	C	C	C	C	C	C	C	A	A	B
Ethylene Chloride*#		C	C	C	C	C	C	C	C	A	B	A	A	B	C
Ethylene Glycol*		A	A	A	A	A	A	A	A	A	A	A	A	A	B
Fatty Acids*		A	A	A	A	A	A	B	B	C	B	A	A	B	A
Ferric Chloride	sat'd	A	A	A	A	A	A	A	A	A	B	A	C	A	B
Ferric Nitrate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	B
Ferrous Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	C	A	B
Ferrous Sulphate		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Fish Solubles*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Fluoboric Acid		A	A	A	A	A	A	A	A	A	A	A	C	C	A
Fluosillic Acid	conc.	A	B	A	B	A	A	A	A	A	A	A	B	C	A
Fluosillic Acid	32%	A	A	A	A	A	A	A	A	A	A	A	B	C	A
Formic Acid	all concentr.	A	A	A	A	A	A	A	A	A	A	C	C	C	A
Fructose	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Fruit Pulp*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Furtural #	100%	B	C	C	C	C	C	C	C	B	C	C	B	B	A

REAGENT	CONC.	TANK MATERIALS						FITTING MATERIALS							
		LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Furfuryl Alcohol*#		B	C	C	C	C	C	A	A
Gallic Acid*	sat'd	A	B	A	A	A	A	A	B	B	B	A	B	A	B
Gasoline*#		B	C	B	C	A	C	C	C	C	B	A	A	A	A
Glucose		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycerine*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycol*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Glycolic Acid*	30%	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Grape Sugar	sat'd ag.	A	A	A	A	A	A	A	A	A	A	A	A	A	A
n-Heptane*#		B	B	A	C	C	A	C	A	A	A	A	A
Hexachlorobenzene		A	A	A
Hexanol, Tertiary*		A	A	A	A	B	A	A	...
Hydrobromic Acid	50%	A	A	A	A	A	A	A	A	A	B	A	C	A	B
Hydrochloric Acid	all conc.	A	A	A	A	A	A	A	A	A	...	A	C	C	A
Hydrocyanic Acid	sat'd	A	A	A	A	A	A	A	...	A	C	B	...
Hydrofluoric Acid*	60%	A	A	A	A	A	A	A	A	A	...	A	C	C	A
Hydrogen	100%	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Hydrogen Chloride	dry gas	A	A	A	A	A	A
Hydrogen Peroxide	30%	B	B	A	...	A	A	A	A	A	B	B	A
Hydrogen Peroxide	10%	A	A	A	B	A	A	A	A	A	B	B	A
Hydrogen Sulphide		A	A	A	A	A	A	A	A	A	A	C	B	A	A
Hydroquinone		A	A	A	A	A	A	A	A	...	C	A
Hypochlorous Acid	conc.	A	A	A	A	A	A	A	A	A	...	A	A
Inks #		A	A	A	A	A	A	A	A	A	C	A	A
Iodine +	in k1 sol'n	B	B	C	C	C	B	C	A	C	C	B
Isopropyl Alcohol	100%	A	A	A	A	A	A	...	A	A	A	A	A
Lead Acetate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Lead Nitrate		A	A	A	A	A	A	A	A	A	A	A	A
Lactic Acid*	20%	A	A	A	A	A	A	A	A	A	A	A	B	B	B

REAGENT	CONC.	TANK MATERIALS						FITTING MATERIALS							
		LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Linseed Oil*	100%	B	C	A	A	A	C	A	A	...	A	A	A	A	A
Magnesium Carbonate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Magnesium Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Magnesium Hydroxide	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Magnesium Nitrate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Magnesium Sulphate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Mercuric Chloride	40%	A	A	A	A	A	A	A	A	A	A	A	C	A	C
Mercuric Cyanide	sat'd	A	A	A	A	A	A	B	A	...	A	A	C	A	...
Mercury		A	A	A	A	A	A	B	A	A	A	A	A	A	A
Methyl Alcohol*	100%	A	A	A	A	A	A	A	A	B	B	C	A	A	C
Methylethyl Ketone*#	100%	B	C	A	B	B	C	C	C	A	C	C	A	A	A
Methylene Chloride*#	100%	C	C	B	...	C	C	C	C	C	C	C	A	A	B
Milk		A	A	A	A	C	C	A	A	A	A	A	A	A	A
Mineral Oils #		B	C	A	B	A	C	A	A	A	A	A	A	A	A
Molasses		A	A	A	A	A	A	A	A	C	A	A	A	A	A
Naphtha*#		B	C	B	C	A	A	C	C	A	A	A	A
Naphthalene*#		B	...	A	A	C	C	C	C	C	C	A	A	A	A
Nickel Chloride	conc.	A	A	A	A	A	A	A	A	A	A	A	C	A	B
Nickel Nitrate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	B	B
Nickel Sulphate	conc.	A	A	A	A	A	A	A	A	A	A	A	B	B	B
Nicotine*	dilute	A	A	A	A	A	A	A	A						
Nitric Acid	0-30%	A	A	C	C	A	A	A	A	B	A	A	A	A	A
Nitric Acid +	30-50%	A	B	C	C	A	B	B	B	B	A	A	A	A	A
Nitric Acid +	70%	A	B	C	C	A	B	C	C	C	A	A	A	A	A
Nitric Acid +	95-98%	C	C	C	C	C	C	C	C	C	...	A	A	A	A
Nitrobenzene*#	100%	C	C	C	C	C	C	C	C	C	C	B	A	A	C
n-Octane		A	A	A	A

TANK MATERIALS								FITTING MATERIALS							
REAGENT	CONC.	LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Oleic Acid		B	C	A	B	A	C	C	A	B	C	B	B	C	B
Oxalic Acid*	sat'd	A	A	A	B	A	A	A	C	A	B	A	B	C	B
Perchloroethylene#		C	C			C	C	C	B	C	C	A	A	A	B
Phosphoric Acid	95%	A	A	A	A	A	B	B	A	B	B	A	B	B	A
Photographic Solutions		A	A	A	A	A	A	A	A	B	A	A	A	A	A
Plating Solutions*															
Brass		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Cadium		A	A	A	A	A	A	A	A	C	C	A	A	C	A
Chromium		A	A	A	A	A	A	A	A	...	B	A	C	C	C
Copper		A	A	A	A	A	A	A	A	...	A	A	A	A	A
Gold		A	A	A	A	A	A	A	A	...	A	A	A	A	A
Indium		A	A	A	A	A	A	A	A	...	A	A
Lead		A	A	A	A	A	A	A	A	A	C	C	A
Nickel		A	A	A	A	A	A	A	A	A	C	A	C
Rhodium		A	A	A	A	A	A	A	A	A	A	C	A
Silver		A	A	A	A	A	A	A	A	A	C	C	A
Tin		A	A	A	A	A	A	A	A	A	C	A	A
Zinc		A	A	A	A	A	A	A	A	...	A	A	C	A	B
Potassium Bicarbonate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Bromide	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Bromate	10%	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Carbonate		A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Chlorate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Chromate	40%	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Cyanide	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B

TANK MATERIALS								FITTING MATERIALS							
REAGENT	CONC.	LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Potassium Dichromate	40%	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Ferri/Ferro Cyanide	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Fluoride		A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Hydroxide	conc.	A	A	A	A	A	A	A	A	A	B	B	B	A	B
Potassium Nitrate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Perborate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Perchlorate	10%	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Permanganate	20%	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Persulphate	sat'd	A	A	A	A	A	A	A	A	A	B	A	B
Potassium Sulphate	conc.	A	A	A	A	A	A	A	A	A	C	A	B	A	B
Potassium Sulphide	conc.	A	A	A	A	A	A	A	A	A	C	A	B	A	B
Potassium Sulphite	conc.	A	A	A	A	A	A	A	A	A	C	A	B	A	B
Propargyl Alcohol*		A	A	A	A
n-Propyl Alcohol*		A	A	A	A	A	A	A	A	A	A	A	A
Propylene Dichloride*#	100%	C	C	C	C	C	C	A	A	C	A	B
Propylene Glycol*		A	A	A	A	C	C	A	B	A	B
Pyridine*		A	...	A	...	A	C	C	B	B	C	C	A	B	B
Resorcinol	sat'd	A	A	A	A
Salicylic Acid	sat'd	A	A	A	A	A	A	A	A	A	A	A	A
Sea Water		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Selenic Acid		A	A	A	A	A	A	A
Shortening*		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Silver Nitrate Solution		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Soap Solution*	any con	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Acetate	sat'd	A	A	A	A	A	A	B	B	A	B	C	B	A	A

TANK MATERIALS								FITTING MATERIALS							
REAGENT	CONC.	LDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		LMDPE	HDPE	70°	140°	70°	140°	70°	140°						
Sodium Benzoate	35%	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Biscarbonate	sat'd	A	A	A	A	A	A	A	A	A	B	C	B	B	B
Sodium Bisulphate	sat'd	A	A	A	A	A	A	A	A	A	C	A	B	B	A
Sodium Bisulphite	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	B	A
Sodium Borate		A	A	A	A	A	A	A	A	A	A	A	B	A	A
Sodium Bromide	dilute	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Carbonate	conc	A	A	A	A	A	A	A	A	A	A	C	A	A	A
Sodium Chlorate	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Sodium Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	C	A	A
Sodium Cyanide		A	A	A	A	A	A	A	A	A	A	A	B	A	A
Sodium Dichromate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Ferri/Ferro Cyanide	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Sodium Fluoride	sat'd	A	A	A	A	A	A	A	A	A	C	A	C	A	A
Sodium Hydroxide	conc.	A	A	A	A	A	A	A	A	A	B	A	B	B	B
Sodium Hypochlorite		A	A	A	B	B	B	B	B	B	C	A	C	C	B
Sodium Nitrate		A	A	A	A	A	A	A	A	A	B	A	B	A	B
Sodium Sulphate		A	A	A	A	A	A	A	A	A	B	A	B	A	B
Sodium Sulphide	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Sodium Sulphite	sat'd	A	A	A	A	A	A	A	A	A	A	A	B	A	B
Stannic Chloride	sat'd	A	A	A	A	A	A	A	A	B	C	A	C	A	B
Stannous Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	B
Starch Solution*	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Stearic Acid*	100%	A	A	A	A	A	A	A	B	B	B	B	A	A	B
Sulphuric Acid	0-50%	A	A	A	B	A	A	A	A	B	C	A	C	C	B
Sulphuric Acid	70%	A	B	A	B	A	B	A	A	B	C	A	C	C	B
Sulphuric Acid +	80%	A	C	C	C	A	B	A	A	B	...	A	C	C	B
Sulphuric Acid +	96%	B	C	C	...	A	B	C	B	B	C	A	C	C	B

TANK MATERIALS								FITTING MATERIALS							
REAGENT	CONC.	LDPE LMDPE HDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316 SS	TITANIUM	HASTELLOY C
		70°	140°	70°	140°	70°	140°								
Sulphuric Acid +	98-conc.	B	C	C	...	B	C	C	B	B	C	A	C	C	B
Sulphuric Acid +	fuming	C	C	C	C	C	C	C	B	C	C	A	C	C	C
Sulphurous Acid		A	A	A	A	A	A	A	A	B	C	A	B	A	B
Tallow #		A	...	A	A	A	B	A	A
Tannic Acid*	sat'd	A	A	A	A	A	A	A	A	A	B	A	A	A	B
Tartaric Acid		A	A	A	A	A	A	A	A	B	B	A	C	A	B
Tetrohydrofuran*#		B	C	C	C	C	C	C	C	B	C	C	A	A	A
Titanium Tetrachloride*	sat'd	C	C	C	A
Toluene*		B	B	C	C	C	C	C	C	C	C	C	A	A	A
Trichloroethylene*#		C	C	C	C	C	C	C	C	C	C	A	B	A	B
Triethylene Glycol*		A	A	A	A	A	A	A
Trisodium Phosphate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Turpentine #		C	C	C	C	C	C	B	B	C	C	A	A	B	B
Urea	30%	A	A	A	A	A	A	B	B	A
Urine		A	A	A	A	A	A	A	A	A	C	A	A
Vanilla Extract*		A	A	A	A	A	A
Vinegar		A	A	A	A	A	A	A	A	A	C	A	A	A	A
Water		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Wetting Agent*		A	A	A	A	A	A
Whiskey*		A	A	A	A	C	C	A	A	A	A	A	A	A	A
Wines*		A	A	A	A	A	C	C	A	A	A	A	A	A	A
Xylene #		C	C	C	C	C	C	C	C	C	C	C	A	A	A
Yeast		A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Bromide	sat'd	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Carbonate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Chloride	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Oxide	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A
Zinc Stearate		A	A	A	A	A	A	A	A	A	A	A	A

REAGENT	CONC.	TANK MATERIALS						FITTING MATERIALS							
		LDPE		PP		XLPE		PVC	CPVC	EPDM	NEOPRENE	VITON	316	TITANIUM	HASTELLOY C
		LMDPE	HDPE	70°	140°	70°	140°	70°	140°				SS		
Zinc Sulphate	sat'd	A	A	A	A	A	A	A	A	A	A	A	A	A	A

- * Stress-crack agent - Certain surface active materials, although they have no chemical effect on polyethylene, can accelerate the cracking of polyethylene when it is under stress. Although our tanks are generally stress-free, caution should be used when large tanks are unsupported, and welded fittings are used.
 - # Plasticizer - Certain types of chemicals are absorbed to varying degrees by polyethylene, causing swelling, weight gain, softening, and some loss of yield strength. These plasticizing materials cause no actual chemical degradation of the resin. Some of these chemicals have a strong plasticizing effect (e.g. aromatic hydrocarbons benzene), whereas others have weaker effects (e.g. gasoline). Certain plasticizers are sufficiently volatile that if they are removed from contact with the polyethylene, the part will “dry” out and return to it’s original condition with no loss of properties.
 - + Oxidizers - Oxidizers are the only group of materials capable of chemically degrading polyethylene. The effects on the polyethylene may be gradual even for strong oxidizers, and short term effects may not be measurable. However, if continuous, long-term exposure is intended, the chemical effects should be checked.
- (1) Welded tank connections are not recommended.

CODE:

- (A) Resistant, no indication that serviceability would be impaired.
- (B) Variable resistance, depending on conditions of use.
- (C) Unresistant, not recommended for service applications under any conditions
- (...) Information not yet available.

Have questions? Our trained and friendly staff is here to answer them for you. Call us today!

www.clarionmunicipal.com or call us at : (+1) 863-261-8388 | info@oneclarion.com

© 2023 One Clarion. All rights reserved. One Clarion terms and conditions apply.

